



Adhesives

LVT

Milliken

ADHESIVE TYPE	RH LEVEL	ADHESIVE	LVT TYPE
ROLL-ON/ TROWEL 	up to 98%	LVT Standard <ul style="list-style-type: none"> For on-grade installations vapor retarder required Approved for all grade renovations where concrete pH levels are between 5-12 and RH is less than 99% INSTALL 45 days after new pour with RH testing	2.5 mm & 5 mm FLEXFORM™ LVT
	over 98%	LVT Moisture XT with Acousti-Loc Technology <ul style="list-style-type: none"> For use where very high moisture is a concern NO vapor retarder is required NO moisture testing is required NO RH or pH limits INSTALL 45 days after new pour / NO testing required	2.5 mm & 5 mm FLEXFORM™ LVT
SPRAY 	up to 98%	Mosaic 98 - Spray <ul style="list-style-type: none"> Approved for all grade renovations where concrete pH levels are between 5-12 and RH is equal to or less than 98%. INSTALL 45 days after new pour with RH testing	2.5 mm & 5 mm FLEXFORM™ LVT
	over 98%	Mosaic Moisture XT-Spray <ul style="list-style-type: none"> For use where very high moisture is a concern. NO moisture testing is required. NO RH or pH limits. NO vapor retarder is required. INSTALL 45 days after new pour / NO testing required	5 mm FLEXFORM™ LVT